[45] Oct. 28, 1975

[54]	CONTACT	Γ LENS	
[75]	Inventor:		
[73]	Assignee:	High Voltage Engineering Corporation, Burlington, Mass.	
[22]	Filed:	Dec. 4, 1972	
[21]	Appl. No.:	311,819	
Related U.S. Application Data			
[63]	Continuation-in-part of Ser. No. 151,377, June 9, 1971, abandoned, and a continuation-in-part of Ser. No. 172,538, Aug. 17, 1971, abandoned, and a continuation-in-part of Ser. No. 299,711, Oct. 24, 1972, abandoned.		
	2		
[51]	Int. Cl. <sup>2</sup>	G02C 7/04; C08F 2/54	
[58]	Field of Sea	arch 351/160; 117/93.31, 138.8 A; 260/827; 204/159.13, 159.15; 264/1, 22; 156/272	
[56]		References Cited	
UNITED STATES PATENTS			
2,339,4 2,479,9 3,179,5 3,700,5 3,700,7 3,745,0 3,750,2	35 8/1949 46 4/1969 73 10/1972 61 10/1972 42 7/1973	9 Johnson 264/1   5 Fischer 156/272   2 Laizier 204/159.13   2 O'Driscoll 351/160 X   3 Lim 117/138.8 A	

## FOREIGN PATENTS OR APPLICATIONS

1,045,665 10/1966 United Kingdom...... 351/160

## OTHER PUBLICATIONS

Yasuda et al., "Graft Copolymerization of Vinylpyrrolidone Onto Polydimethylsiloxane," *Journal of Polymer Science*, Part A, Vol. 2, pp. 5093–5098, (1964).

Primary Examiner—William D. Martin Assistant Examiner—William H. Schmidt Attorney, Agent, or Firm—Kenway & Jenney

## [57] ABSTRACT

A contact lens comprising a silicon polymer or copolymer core and a hydrophilic polymer surface grafted to the core is formed by contacting a silicone with a free radical polymerizable precursor to the polymer in a liquid state and subjecting the precursor and silicone to a high dose of ionizing radiation for a short period. The radiation dose, time of radiation and temperature are controlled to produce an optically clear contact lens by forming a smooth surface of the polymer grafted to the silicone, preventing substantial migration of the precursor into the silicone and preventing localized high concentration of hydrophilic polymer on the silicone surface. The silicone may be irradiated while immersed in a solution of the precursor or in a mold where the precursor is present as a coating on an inside surface of the mold. The hydrophilic surface may be grafted onto a silicone sheet which is then grafted onto the silicon lens.

## 14 Claims, 12 Drawing Figures